



## FEDRIGONI ARENA® IVORY BULK

### description

Uncoated high thickness papers, with FSC® certification. Available in the bright new “Ivory” shade. Rational yet elegant, good for texts, pictures, and illustrations. It works with any printing and post-printing process and performs well with any binding and folding technique.

### range

size	grain	substance			
64x90	LG	80	90	100	120
72x102	LG	80	90	100	120

### technical features

ref. standard/instrument  
unit of measure

substance	bulk	opacity	roughness	brightness
ISO 536	ISO 534	ISO 2471	ISO 8791-2	ISO 2470
g/m <sup>2</sup>	cm <sup>3</sup> /g	%	ml/min	%
80 ± 3%	1,7	89 ± 2	900 ± 20%	72% ± 3
90 ± 3%	1,7	90 ± 2	950 ± 20%	72% ± 3
100 ± 3%	1,7	91 ± 2	1000 ± 20%	72% ± 3
120 ± 3%	1,7	92 ± 2	1100 ± 20%	72% ± 3
140 ± 3%	1,7	94 ± 2	1200 ± 20%	72% ± 3

Relative Humidity 50% ± 5 ref. TAPPI 502-98

### ecological features



The mark of  
responsible forestry

ELEMENTAL  
CHLORINE  
**FREE**  
GUARANTEED

ACID FREE

HEAVY METAL  
**HM**  
ABSENCE  
C E 9 4 / 6 2

### notes

The product is completely biodegradable and recyclable. Special runs available upon request. Fedrigoni Arena® Ivory Bulk has a bulk of 1.7 and contains CTMP (chemi-themo mechanical pulp) a raw material that allows to obtain higher thicknesses but that can bring slight variations in the shade and occasional small spots from one making to the next compared to Ivory Smooth and Ivory Rough versions.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Fedrigoni Arena® Ivory Bulk is excellent for de luxe publications, diaries, note-books, envelopes, calendars, catalogues and letterheads.

[applications](#)

Fedrigoni Arena® Ivory Bulk can be used without problems with the main printing processes: traditional and UV or H-UV offset, embossing, hot foil stamping, screen printing, letterpress.

The macro-porous surface works best when using semi-oxidative drying inks. Fedrigoni Arena® Ivory Bulk has good chromatic and tone performance.

[printing suggestions](#)

Varnishing and plastic laminating must be assessed in advance. Varnishing applied with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screenprinting varnishing achieves better results, although it's often necessary to perform two runs to achieve best results.

The surface roughness, typical of uncoated papers, may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the paper. Good results are achieved with major processing operations such as cutting, die-cutting, scoring, folding and gluing.

[converting suggestions](#)