

Offset

Facestock

Offset

Description Calendered uncoated woodfree paper.

Applications Ideal for all types of applications: variable label information (barcodes, expiry date, price, weight etc.)

Printing techniques Suitable for printing on flexo (all types), conventional offset, offset UV, letterpress (conventional and UV), screen printing, thermal transfer, laser, hot stamping.

Property	Norm	Units	Value	Tolerance
Substance	75	g/m ²	75	70-76
Thickness	ISO 534	µm	70	± 2
Bekk smoothness	ISO 5627	s	≥ 250	
Brightness ISO	ISO 2470-2	%	101.5	± 2
Whiteness CIE	ISO 11475	%	158.2	± 5
Opacity	ISO 2471	%	89	-2
Tensile strength MD/CD	ISO 1924-2	kN/m	5.0/3.0	-1

Certificates

Product approvals and usage certificates

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Toy safety European directive 2009/48/CE

Packaging and packaging waste Directive 94/62/CE

Electric and electronic equipment (RoHS)

- Values are subject to change without notice. Last updated 1/18/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive is certified to the strictest environmental standards **ISO 9001 and EMAS** and has successfully completed audits for **ISO 50001, ISO 9001 and OHSAS 18001**. Adestor products are available with **PEFC™ and FSC®** chain of custody certificates upon request.