



SYMBOL FREELIFE GLOSS

description Environmentally-friendly ECF papers and boards certify FSC. High content of selected recycled material (minimum quantity guaranteed 25%). Triple blade coated on both sides with a Gloss finish.

range	size	grain	substance									
	45x64	LG	90*	100*	115	130	150	170	200	250	300	
	50x70	LG	90*	100*	115	130	150	170	200	250	300	
	64x88	LG	90*	100*	115	130	150	170	200	250	300	350
	70x100	LG	90*	100*	115	130	150	170	200	250	300	350
	72x102	LG										400
	88x128	LG		100*	115	130	150	170				
	100x140	LG			115	130	150					

* Available upon request

technical features
ref. standard/instrument
unit of measure

	substance	VSA	opacity	gloss	tensile strength	
	ISO 536	ISO 534	ISO 2471	ISO 8254-2	ISO 1924	
	g/m ²	cm ³ /g	%	%	kN/m	
					long±10%	cross±10%
TWO BLADES COATING	90 ± 3%	0,76	91 ± 2	73 ± 10	3,5	2,7
	100 ± 3%	0,77	92 ± 2	73 ± 10	4	3,1
	115 ± 3%	0,70	93 ± 2	73 ± 10	4,5	3,4
	130 ± 3%	0,71	94 ± 2	73 ± 10	5,1	3,8
THREE BLADES COATING	150 ± 3%	0,71	95 ± 2	73 ± 10	5,9	4,4
	170 ± 3%	0,72	-	73 ± 10	6,7	5
	200 ± 4%	0,71	-	73 ± 10	7,1	5,5
	250 ± 5%	0,74	-	73 ± 10	-	-
	300 ± 5%	0,76	-	73 ± 10	-	-
	350 ± 5%	0,80	-	73 ± 10	-	-
	400 ± 5%	0,81	-	73 ± 10	-	-

Brightness - ISO 2470 (R457) - 104% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



The mark of responsible forestry

ELEMENTAL CHLORINE FREE GUARANTEED



notes Given the considerable amount of recycled content within the product it is possible for there to be a slight variation in the shade, from one making to the next. The product is completely bio-degradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Symbol Freeliflife Gloss is excellent for publications, packaging, coordinated graphic materials, covers, inserts and de luxe brochures.

[applications](#)

Symbol Freeliflife Gloss can be used with all the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing.

[printing suggestions](#)

Good results with major processing operations such as: cutting, die-cutting, scoring, folding, glueing, varnishing and plastic lamination. We suggest to scoring all the substances above 170 gsm.

[converting suggestions](#)


S Y M B O LTM