

Technical Data Sheet

Premium Coated Paper 100gr

Product specifications

Product:	MH 1084	Unit	Standard
Basic weight	107 ± 6	g/m ²	ISO 536
Paper thickness	133 ± 7	μm	ISO 534
Opacity	91 ± 3	%	ISO 2471
Stiffness md	9 ± 4	mN	ISO 2493
Stiffness cd	5 ± 3	mN	ISO 2493
Smoothness (fs)	57 ± 20	sec	ISO 5627
CIE Whiteness (fs)	155 ± 5		ISO 11475
Shade (fs) L*	96.5 ± 2		ISO 5631-2
a*	3.9 ± 1		ISO 5631-2
b*	- 14.5 ± 2		ISO 5631-2

Lamination: Cold: Yes Hot: Yes

Processing: Best printing results occur in a standard climate of 23°C and 50% relative humidity. For problem-free running, always store the printing medium in the original packaging and protect it from direct sunlight and moisture.

Suit for:

- Solvent inkjet
- Eco solvent inkjet
- Latex
- Cold over laminating
- UV curable
- Water based inkjet
- Screen printing
- Die Sublimation

Common Applications

- Art Prints, Posters
- Point of sales
- Indoor advertising